

University of Nebraska - Lincoln

## DigitalCommons@University of Nebraska - Lincoln

---

David Sellmyer Publications

Research Papers in Physics and Astronomy

---

May 2002

### Mechanically milled nanostructured (Sm,Pr) $_{12.5}\text{Co}_{85.5}\text{Zr}_2$ magnets with TbCu<sub>7</sub> structure

Hong Tang

*University of Nebraska - Lincoln*

Jian Zhou

*University of Nebraska - Lincoln*

David J. Sellmyer

*University of Nebraska-Lincoln*, [dsellmyer@unl.edu](mailto:dsellmyer@unl.edu)

Follow this and additional works at: <https://digitalcommons.unl.edu/physicssellmyer>



Part of the [Physics Commons](#)

---

Tang, Hong; Zhou, Jian; and Sellmyer, David J., "Mechanically milled nanostructured (Sm,Pr)  $_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnets with TbCu<sub>7</sub> structure" (2002). *David Sellmyer Publications*. 41.

<https://digitalcommons.unl.edu/physicssellmyer/41>

This Article is brought to you for free and open access by the Research Papers in Physics and Astronomy at DigitalCommons@University of Nebraska - Lincoln. It has been accepted for inclusion in David Sellmyer Publications by an authorized administrator of DigitalCommons@University of Nebraska - Lincoln.

# Mechanically milled nanostructured $(\text{Sm},\text{Pr})_{12.5}\text{Co}_{85.5}\text{Zr}_2$ magnets with $\text{TbCu}_7$ structure

Hong Tang,<sup>a)</sup> Jian Zhou, and David J. Sellmyer

*Department of Physics and Astronomy, and Center for Materials Research and Analysis, University of Nebraska, Lincoln, Nebraska 68588-0113*

Nanostructured  $(\text{Sm},\text{Pr})(\text{Co},\text{Zr})$  magnets with the  $\text{TbCu}_7$ -type structure have been synthesized by mechanically milling  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  alloys ( $0 \leq x \leq 0.8$ ) followed by appropriate annealing. Magnetic properties, structure, and microstructure have been investigated. It is found that single-phase  $(\text{Sm},\text{Pr})(\text{Co},\text{Zr})_7$  magnets with the  $\text{TbCu}_7$  structure and with nanoscale grain size (14–19 nm) form in the whole composition range. Intrinsic coercivity  $H_{ci}$  decreases from 20.7 to 5.6 kOe with increasing Pr content from 0 to 0.8, while energy products  $(\text{BH})_{\text{max}}$  shows an optimum value of 12.6 MGOe ( $H_{ci}$  of 17.9 kOe) at  $x=0.2$  due to increase in remanent magnetization. Remanence ratio is observed in the range of 0.64–0.69, with an optimum value of  $\sim 0.69$  at  $x=0.3$ . The high coercivity is ascribed to the formation of nanocrystalline  $(\text{Sm},\text{Pr})(\text{Co},\text{Zr})_7$  phase of the  $\text{TbCu}_7$ -type structure with large anisotropy, and the remanence enhancement may result from the exchange-coupling interactions between nanosized  $(\text{Sm},\text{Pr})(\text{Co},\text{Zr})_7$  grains. The magnetic properties can be understood in term of the anisotropy of the magnetically hard phase and the interactions between the nanosized grains. © 2002 American Institute of Physics. [DOI: 10.1063/1.1447509]

## I. INTRODUCTION

Co-based permanent rare-earth magnets have attracted much attention<sup>1,2</sup> recently during the process of search for permanent magnets applicable at high temperatures, owing to its high Curie temperature and high magnetic performance. It is well known that the 1:7 phase with  $\text{TbCu}_7$ -type structure plays an important role in the development of cellular-structure  $\text{Sm}(\text{Co},\text{Fe},\text{Cu},\text{Zr})$  magnets which possess high coercivity.<sup>1</sup> It was also reported two decades ago that  $\text{Sm}(\text{Co},\text{Fe},\text{Cu},\text{Zr})_z$  magnets with the 1:7 composition exhibited better temperature dependence of coercivity than that of the 2:17 counterpart.<sup>3</sup> Recently, it has been reported that R–Co (R=Sm,Pr, etc.) alloys with the  $\text{TbCu}_7$  type structure could be achieved by introducing a small amount of stabilizing elements like Zr or Ti.<sup>4–6</sup> These alloys with 1:7 composition and the  $\text{TbCu}_7$  structure possess high Curie temperature, high magnetization, and exhibit large anisotropy.<sup>4–6</sup> For example, anisotropy field values up to  $\sim 160$  and  $\sim 100$  kOe at room temperature were reported for the  $\text{Sm}(\text{Co},\text{Zr})_7$  alloys<sup>4</sup> and  $\text{Pr}(\text{Co},\text{Zr})_7$  alloys<sup>5</sup> with a small amount of Zr, respectively. Therefore, good high temperature magnetic performance may be expected in the nanostructured R–Co magnets (R=Sm, Pr) with  $\text{TbCu}_7$  structure.

Mechanical milling or mechanical alloying have been proven to be a powerful technique in the fabrication of nanostructured Co-based magnets.<sup>7,8</sup> Some previous researches<sup>9,10</sup> have shown that high coercivity ( $H_{ci}$ ) could be obtained in the mechanically milled nanostructured  $\text{Sm}(\text{Co},\text{Zr})_7$  magnets with the  $\text{TbCu}_7$ -type structure.  $H_{ci}$  value as high as 5.3 kOe was also reported in the mechanically milled  $\text{Pr}(\text{Co},\text{Zr})_7$  magnets<sup>11</sup> (low Zr content) with  $\text{TbCu}_7$ -type structure. Compared with the Sm counterpart,  $\text{Pr}(\text{Co},\text{Zr})_7$  alloys with

$\text{TbCu}_7$  structure possess higher magnetization (above 110 emu/g)<sup>5</sup> than  $\text{Sm}(\text{Co},\text{Zr})_7$  alloys ( $\sim 92$  emu/g)<sup>4</sup> with a small amount of Zr, whereas the alloy retains a high anisotropy field value of up to 100 kOe.<sup>5,11</sup> Therefore, high coercivity and optimum energy products [ $(\text{BH})_{\text{max}}$ ] could be expected in nanostructured  $(\text{Sm},\text{Pr})(\text{Co},\text{Zr})_7$  alloys with a small amount of Zr. Our previous investigations on mechanically milled  $\text{Sm}_{12.5}\text{Co}_{87.5-x}\text{Zr}_x$  magnets have indicated that high  $H_{ci}$  and optimum  $(\text{BH})_{\text{max}}$  could be achieved with  $x=2$  after appropriate processing.<sup>10,12</sup> In this study, we focus on the nanostructured  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  ( $x=0-0.8$ ) magnets synthesized by means of mechanical milling followed by appropriate annealing. Optimum  $(\text{BH})_{\text{max}}$  of 12.6 MGOe (with  $H_{ci}$  of 17.9 kOe) is obtained with  $x=0.2$ .

## II. EXPERIMENT

$(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  ( $x=0.0, 0.1, 0.2, 0.3, 0.5, 0.8$ ) alloys were prepared by arc melting the constituent elements with at least 99.9% purity. After grinding into powders with particle size of less than 0.1 mm, the alloy powders were mechanically milled in a Spex 8000 Mill for a period of 5 h in an atmosphere of high-purity argon gas. The ball-to-powder mass ratio was fixed at 8:1. The powders were handled in a glove box under protection of high-purity argon gas. The milled powders were then sealed in quartz tubes after being evacuated and then backfilled with high-purity argon gas. The sealed powders were annealed at 650 °C for 20 min then furnace cooled to room temperature. The phase and structure were characterized with x-ray diffraction (XRD) with  $\text{Cu K}\alpha$  radiation. The microstructure was investigated with transmission electron microscopy (TEM). The magnetic properties were measured at room temperature (295 K) using a superconducting quantum interference device (SQUID) magnetometer with a field range of  $\pm 55$  kOe.

<sup>a)</sup> Author to whom correspondence should be addressed; present address: Ames Laboratory, Iowa State University, Ames, IA 50011-3020.




FIG. 1. XRD patterns for the mechanically milled and annealed  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnets.

### III. RESULTS AND DISCUSSION

Figure 1 shows the XRD patterns for the milled  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnets after annealing at 650 °C for 20 min. It shows that all the milled and annealed powder samples are basically of single phase with  $\text{TbCu}_7$ -type structure, although the corresponding as-cast alloys are not of single phase (mixture of  $\text{TbCu}_7$  phase and  $\text{Th}_2\text{Zn}_{17}$  phase) for  $x > 0.3$ . The lattice parameters of the  $\text{TbCu}_7$ -type phase obtained by fitting the XRD patterns are listed in Table I. The lattice parameters are consistent with the reports<sup>4,5</sup> for  $\text{Sm}(\text{Co,Zr})_7$  and  $\text{Pr}(\text{Co,Zr})_7$  as-cast alloys with appropriate Zr content. With variation of Pr, parameters  $a$ ,  $c$  and the ratio  $c/a$  vary slightly.

The broadening of the diffraction peaks results from nanosized grains. The grain sizes  $d$  estimated using the Scherrer formula are listed in Table I. It is seen that the grain size is in the range of 14–19 nm. The nanostructure developed after milling and annealing is supported by the TEM investigations. Figure 2 shows the TEM image for the milled and annealed  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnet powders with  $x = 0.0$ . The inset is the selected-area electron diffraction rings, which exhibits the nature of single phase with




FIG. 2. TEM image for mechanically milled  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  ( $x = 0.0$ ) magnets.

$\text{TbCu}_7$ -type structure. From TEM image, the nanostructure with grain size of  $\sim 15$  nm is obvious, which is in good agreement with the XRD estimate.

Figure 3 shows the magnetization curves and magnetic hysteresis loops at room temperature for the milled and annealed  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnet powders. It is clear that high  $H_{ci}$  values are realized in these nanostructured magnet powders. Hard magnetic property parameters [ $H_{ci}$ ,  $M_r$ ,  $M_r/M_s$  and  $(\text{BH})_{\text{max}}$ ] are listed in Table I. The saturation magnetization values ( $M_s$ ) are obtained by fitting the high-field portion of the initial magnetization curves in terms of an approach-to-saturation law containing a term proportional to  $H^{-2}$ . The  $M_s$  values for the two end compositions are in good agreement with the reported values<sup>4,5</sup> for as-cast alloys ( $\text{TbCu}_7$  type phase) with suitable Zr content. The dependence of hard magnetic property parameters is replotted against Pr content, as shown in Fig. 4. It is obvious that  $H_{ci}$  decreases from 20.7 to 5.6 kOe as the Pr content varies from  $x = 0.0$  to  $x = 0.8$ , and correspondingly  $M_r$  increases.  $(\text{BH})_{\text{max}}$  exhibits an optimum value of 12.6 MGOe at  $x = 0.2$ . The  $H_{ci}$  value for the end composition with  $x = 0.8$  is still higher than the reported for nanostructured  $\text{Pr}(\text{Co,Zr})_7$  magnets with  $\text{TbCu}_7$  structure.<sup>11</sup> The  $M_r/M_s$  ratio, being in the range of 0.64–0.69, is much higher than that of ideally isotropic hard-magnetic particles (0.5).

The high coercivity is ascribed to the nanostructure of the  $(\text{Sm,Pr})(\text{Co,Zr})_7$  phase with high anisotropy.<sup>2</sup> Generally,

TABLE I. Hard magnetic properties [ $H_{ci}$ ,  $M_r$ ,  $M_s$  and  $(\text{BH})_{\text{max}}$ ], lattice parameters ( $a$ ,  $c$ , and  $c/a$  ratio) and grain size ( $d$ ) for the  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnets.

$x$	Hard magnetic property parameters					Lattice parameters			
	$H_{ci}$ (kOe)	$M_r$ (emu/g)	$M_s$ (emu/g)	$M_r/M_s$	$(\text{BH})_{\text{max}}$ (MGOe)	$d$ (nm)	$a$ (Å)	$c$ (Å)	$c/a$
0.0	20.7	63.2	97.7	0.647	11.1	14.2	4.878	4.053	0.831
0.1	18.4	62.9	95.9	0.656	10.8	18.2	4.876	4.073	0.835
0.2	17.9	68.7	104.5	0.658	12.6	16.4	4.881	4.078	0.835
0.3	10.5	70.7	103.4	0.683	12.2	15.8	4.865	4.067	0.836
0.5	11.1	69.9	102.6	0.682	11.5	15.2	4.884	4.073	0.834
0.8	5.6	74.9	117.1	0.639	9.4	15.8	4.887	4.079	0.835




FIG. 3. Magnetization curves and magnetic hysteresis loops for mechanically milled  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnets.

coercivity of hard magnets can be expressed as

$$H_c = (2K_1/M_s)\alpha_K - N_{\text{eff}}M_s,$$

where  $K_1$  and  $M_s$  are the anisotropy constant and the saturation magnetization of the material and  $\alpha_K$  and  $N_{\text{eff}}$  are microstructure-dependent factors describing the effect of the microstructure on the crystal field and the local internal dipolar field. With increasing Pr content, the anisotropy of the  $\text{TbCu}_7$  type phase decreases. Therefore the coercivity variation with Pr content is understandable. The increase of  $M_r$  with Pr content is consistent with the fact that  $\text{Pr}(\text{Co,Zr})_7$  possess higher  $M_s$  value than  $\text{Sm}(\text{Co,Zr})_7$ <sup>4,5</sup> since  $\text{Pr}^{3+}$  has a higher moment.

The remanence enhancement in the nanostructured  $(\text{Sm,Pr})(\text{Co,Zr})_7$  magnet powders indicates exchange-coupling interactions between the nanosized grains.<sup>2,7,8</sup> Taking into account this point together with the shape of initial magnetization curve (Fig. 3), it seems that the underlying




FIG. 4. Hard magnetic property dependence on Pr content for the  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  magnets.

mechanism for the coercivity changes from a pinning type to a mixture of pinning and nucleation.<sup>1,2</sup> However, considering the fact of stronger interactions between the nanosized grains (below 20 nm), the interaction among the domains of the adjacent particles may lead to the formation of “interaction domains.” The coercivity in this system is probably controlled by the motion of domain walls in the “interaction domains.”<sup>2</sup>

#### IV. CONCLUSIONS

Nanostructured  $(\text{Sm,Pr})_{12.5}(\text{Co,Zr})_{87.5}$  magnets with the  $\text{TbCu}_7$ -type structure have been synthesized by mechanically milling  $(\text{Sm}_{1-x}\text{Pr}_x)_{12.5}\text{Co}_{85.5}\text{Zr}_2$  alloys ( $0 \leq x \leq 0.8$ ) followed by appropriate annealing. Single-phase  $(\text{Sm,Pr})(\text{Co,Zr})_7$  magnets with the  $\text{TbCu}_7$  structure and with nanosized grains (14–19 nm) form in the whole composition range. High  $H_{ci}$  values are realized in the range of 20.7–5.6 kOe with varying Pr content from 0 to 0.8, while  $(\text{BH})_{\text{max}}$  shows an optimum value of 12.6 MGOe ( $H_{ci}$  remains 17.9 kOe) at  $x=0.2$ . Remanence ratio in the range of 0.64–0.69 is observed with an optimum value 0.69 at  $x=0.3$ . The high coercivity is ascribed to the formation of nanostructured  $(\text{Sm,Pr})(\text{Co,Zr})_7$  phase of the  $\text{TbCu}_7$ -type structure with large anisotropy, and the remanence enhancement may result from the exchange-coupling interactions between the adjacent nanosized  $(\text{Sm,Pr})(\text{Co,Zr})_7$  grains. The magnetic properties can be understood by taking into account the anisotropy of the hard phase and the interactions between the nanosized grains.

#### ACKNOWLEDGMENTS

This work was supported by DARPA/ARO and AFOSR. We are grateful to Dr. Y. Liu for his assistance in TEM experiments.

- <sup>1</sup>K. J. Strnat, in *Ferromagnetic Materials*, edited by E. P. Wohlfarth and K. H. J. Buschow (Elsevier Science, Amsterdam, 1988), Vol. 4, p. 131, and references therein.
- <sup>2</sup>G. C. Hadjipanayis, *J. Magn. Magn. Mater.* **200**, 373 (1999), and references therein.
- <sup>3</sup>S. Liu, H. F. Mildrum, and K. J. Strnat, *J. Appl. Phys.* **53**, 2383 (1982).
- <sup>4</sup>M. Q. Huang, W. E. Wallace, M. McHenry, Q. Chen, and B. M. Ma, *J. Appl. Phys.* **83**, 6718 (1998).
- <sup>5</sup>M. Q. Huang, M. Drennan, W. E. Wallace, M. E. McHenry, Q. Chen, and B. M. Ma, *J. Appl. Phys.* **85**, 5663 (1999).
- <sup>6</sup>J. Zhou, I. A. Al-Omari, J. P. Liu, and D. J. Sellmyer, *J. Appl. Phys.* **87**, 5299 (2000).
- <sup>7</sup>P. G. McCormick, *Handbook on the Physics and Chemistry of Rare Earths*, edited by K. A. Gschneidner, Jr. and L. Eyring (Elsevier Science, Amsterdam, 1997), Vol. 24, p. 47, and references therein.
- <sup>8</sup>P. G. McCormick, W. F. Miao, P. A. I. Smith, J. Ding, and R. Street, *J. Appl. Phys.* **83**, 6256 (1998).
- <sup>9</sup>Z. M. Chen, X. Meng-Burany, H. Okumura, and G. C. Hadjipanayis, *J. Appl. Phys.* **87**, 3409 (2000).
- <sup>10</sup>H. Tang, Y. Liu, and D. J. Sellmyer, *J. Magn. Magn. Mater.* (to be published).
- <sup>11</sup>Z. M. Chen, X. Meng-Burany, and G. C. Hadjipanayis, *J. Appl. Phys.* **87**, 5302 (2000).
- <sup>12</sup>H. Tang, J. Zhou, Y. Liu, and D. J. Sellmyer, *Mater. Res. Soc. Symp. Proc.* **644**, L8.4 (2000).